

**RESIN INFORMATION SHEET**

Product Name TOYOPEARL® AF-Heparin HC-650M
(Functionalised resin for affinity chromatography)

Part Numbers

| | |
|---------|--------------------------------------|
| 0020030 | TOYOPEARL AF-Heparin HC-650M, 10 mL |
| 0020031 | TOYOPEARL AF-Heparin HC-650M, 100 mL |
| 0020032 | TOYOPEARL AF-Heparin HC-650M, 1 L |
| 0020033 | TOYOPEARL AF-Heparin HC-650M, 5 L |

Product Description TOYOPEARL chromatographic resins are based on a rigid methacrylic polymer, resulting in high mechanical and chemical stability. Resins are available as non-functionalized “HW” series resins for size exclusion separations, and derivatized with surface chemistries for alternative modes of chromatography such as ion exchange, hydrophobic interaction or affinity separations.

TOYOPEARL AF-HeparinHC-650M is a functionalised support resin for affinity chromatography. The material is prepared by introducing porcine intestinal mucosa heparin onto TOYOPEARL HW-65. TOYOPEARL AF-Heparin HC-650M is useful for the chromatographic purification of blood coagulation factors, complement, DNA or RNA polymerases, lipoproteins and other similar target molecules.

| | | |
|-----------------------------|------------------------------|---|
| Operating Conditions | Packing pressure | Typically 0.3 MPa |
| | Shipping solvent | 20 % (v/v) ethanol |
| | Shipping formulation | 72 % (v/v) slurry in shipping solvent (*) |
| | Pressure limiting factor | Depend on column hardware (typically 0.7 MPa) |
| | Operating linear flowrate | Typically 10 - 600 cm/hour |
| | Long-term storage conditions | 20 % (v/v) ethanol at 2 - 8 °C |

| | | |
|-----------------------|--|------------------|
| Specifications | Particle size distribution (min. 80 % within range) | 40 - 90 µm |
| | AT-III adsorption capacity | Min. 5 g/L - gel |
| | Bacterial count | Max. 100 CFU/mL |
| | Endotoxin concentration | Max. 10.0 EU/mL |
| | Foreign substance (colored particle) | Unobserved |

| | | |
|-------------------------------|---------------------------------|--|
| Additional Information | Appearance | White resin slurry which settles upon standing |
| | Mean pore diameter (base resin) | 100 nm (*) |

(*) The value is for reference only, not guaranteed.

Lot-specific data are included in the Certificate of Analysis (COA) shipped with the product.
For detailed test procedures please refer to the appropriate Regulatory Support File.