



## RESIN INFORMATION SHEET

**Product Name** TOYOPEARL® MegaCap II SP-550EC  
(Strong cation exchange chromatography resin)

<b>Part Numbers</b>	0021804	TOYOPEARL MegaCap II SP-550EC, 100 mL
	0021805	TOYOPEARL MegaCap II SP-550EC, 250 mL
	0021806	TOYOPEARL MegaCap II SP-550EC, 1 L
	0021807	TOYOPEARL MegaCap II SP-550EC, 5 L
	0021808	TOYOPEARL MegaCap II SP-550EC, 50 L

**Product Description** TOYOPEARL chromatographic resins are based on a rigid methacrylic polymer, resulting in high mechanical and chemical stability. Resins are available as non-functionalized “HW” series resins for size exclusion separations, and derivatized with surface chemistries for alternative modes of chromatography such as ion exchange, hydrophobic interaction or affinity separations.

TOYOPEARL MegaCap II SP-550EC chromatographic resin is designed for cation exchange chromatography of peptides and small proteins. This chromatographic mode separates molecules on the basis of ionic interactions between the sample and the resin. The separation is usually accomplished in buffered aqueous solution with a gradient of increasing ionic strength. Alternatively, pH adjustment may be used for control of elution.

<b>Operating Conditions</b>	Packing pressure	Typically 0.3 MPa
	Shipping solvent	20 % (v/v) ethanol
	Shipping formulation	72 % (v/v) slurry in shipping solvent (*)
	Pressure limiting factor	Depend on column hardware (typically 0.7 MPa)
	Operating linear flowrate	Typically 10 - 3000 cm/hour
	Long term storage conditions	20 % (v/v) ethanol
	Cleaning in place / sanitization	0.1 - 0.5 mol/L NaOH or 0.1 mol/L HCl

<b>Specifications</b>	Particle size distribution (Min. 80 % within range)	100 - 300 µm for EC-grade
	Ion exchange capacity	0.10 -0.20 eq/L
	Insulin adsorption capacity	100 - 155 g/L
	Bacterial count	Max. 100 CFU/mL
	Endotoxin concentration	Max. 10.0 EU/mL
	Eluable matter	Max. 0.2 % (for dry gel)
	Foreign substance (colored particle)	Max. 6

<b>Additional Information</b>	Appearance	White resin slurry which settles upon standing
	Mean pore diameter (base resin)	50 nm (*)

(\*) The value is for reference only, not guaranteed.

Lot-specific data are included in the Certificate of Analysis (COA) shipped with the product. For detailed test procedures please refer to the appropriate Regulatory Support File.